eco-INSTITUT Germany GmbH
Laborprüfung
Laboratory testing

NMC s.a.
Gert-Noel-Strasse
4731 Eynatten
Belgien

Test Report No. B57762-A001-AgBB-L

This test report replaces the test report no. 57762-A001-AgBB-L dated 24/11/2022.
(Correction: article designation changed from "normafloor" to "nomafloor")

Test objective:	**Evaluation according to AgBB scheme 2021**
Article designation according to order:	**nomafloor M80** **Tested as a representative for:** - **nmc HDPS skirtings in FINISHED WHITE, COLOURS (RAL/NCS)**
Sample/batch according to order:	**6000032138**
Sampling by:	Zoé Van Rey
Date of sampling:	10/10/2022
Location of sampling:	no information
Date of production:	07/10/2022
Date of report:	15/12/2022
Number of pages of report:	18
Testing laboratory:	eco-INSTITUT Germany GmbH, Köln
Test objective fulfilled:	✓
Note:	The test results in the report refer exclusively to the test sample submitted by the manufacturer. The report is not permitted to be used in product and company advertising. The report may be published in full as technical documentation on the Internet with the written consent of eco-INSTITUT Germany GmbH. eco-INSTITUT Germany GmbH has recommended that the manufacturer repeats the test after 3 years at the latest. More information at www.eco-institut.de/en/advertising

Content

Sample View 2
Statement of conformity with AgBB 2021 3
Summary statement of conformity with AgBB 2021 4
Laboratory report 5
1 Emission analysis 5
1.1 Sample A001, Volatile Organic Compounds after 3 days 6
1.2 Sample A001, Volatile Organic Compounds after 28 days 9
Appendix 12
Sampling sheet 12
List of calibrated Volatile Organic Compounds (VOC) 13
Definition of terms 15
Commentary on emission analysis 17
Explanation of Specific Emission Rate SER 18

Sample View

Internal sample number (assigned by the laboratory)	Article designation according to order	Sample/batch number according to order	Receipt of sample	Condition upon delivery	Type of sample
57762-A001	nomafloor M80	6000032138	13/10/2022	without objection	Skirting



57762-A001

Remark: It is not permitted to publish extracts of this report and the comments on the first page of this report apply.

Statement of conformity with AgBB 2021

The sample with the internal sample number 57762-A001 has been tested on behalf of **NMC s.a.**. The article description according to the order is **nomafloor M80**.

This evaluation is based on the test criteria of the Scheme "Health-related Evaluation of Emissions of Volatile Organic Compounds (VVOC, VOC and SVOC) from Building Products" of the Committee for Health-Related Evaluation of Building Products (AgBB 2021).

The results documented in the test report were evaluated as follows.[1]

Test parameter	Result	Requirement	Requirement hold [yes/no]
Emission analysis			
Measurement time: 3 days after test chamber loading			
Sum VOC (C6-C16) [1)]	< 0.005 mg/m³	≤ 10 mg/m³	yes
Carcinogenic substances, cat. 1A and 1B acc. to Regulation (EC) No. 1272/2008 (and TRGS 905) (per substance)	≤ 0.01 mg/m³	≤ 0.01 mg/m³	yes
Measurement time: 28 days after test chamber loading			
Sum VOC (C6-C16) including SVOC with LCI [1)]	< 0.005 mg/m³	≤ 1.0 mg/m³	yes
Sum SVOC without LCI (C_{16}-C_{22}) [1)]	< 0.005 mg/m³	≤ 0.1 mg/m³	yes
R-value (dimensionless)	0.00	≤ 1	yes
Sum VOC without LCI	< 0.005 mg/m³	≤ 0.1 mg/m³	yes
Carcinogenic substances, cat. 1A and 1B acc. to Regulation (EC) No. 1272/2008 (and TRGS 905) (per substance)	≤ 0.001 mg/m³	≤ 0.001 mg/m³	yes

1) For sum VOC (C_6-C_{16}) and sum SVOC (C_{16}-C_{22}) only substances ≥ 5 µg/m³ are considered.

[1] If a measurement result that slightly exceeds the specification is assessed as "not fulfilled", this is based on the agreement of the "shared risk of measurement uncertainty (shared risk approach)". According to this, the probability that the statement is correct is ≥ 50 %. Similarly, a result slightly below the specification value also only has a probability of ≥ 50 % of being compliant. I.e., the risk of making a false negative statement regarding the fulfilment of the specification is just as high as the risk of making a false positive statement (more information at https://www.eco-institut.de/en/2019/07/measurement_uncertainty/).

Remark: It is not permitted to publish extracts of this report and the comments on the first page of this report apply.

Summary statement of conformity with AgBB 2021

The sample with the internal sample number 57762-A001, article description according to order: **nomafloor M80**, meets the emission requirements of the AgBB scheme.

Cologne, 15/12/2022

M.-A. Dobaj

Marc-Anton Dobaj, M.Sc. Crystalline Materials
(Project management)

Remark: It is not permitted to publish extracts of this report and the comments on the first page of this report apply.

Laboratory report

1 Emission analysis

Test method

DIN EN 16516:2020-10	Testing and evaluation of the release of dangerous substances; determination of emissions into indoor air

A001, Preparation of test sample

Date:	21/10/2022
Sample preparation:	not applicable
Masking of backside:	yes
Masking of edges:	yes, 100 %
Relationship of unmasked edges to surface:	not applicable
Loading:	related to area
Dimensions:	8.75 cm x 1 cm

A001, Test chamber conditions according to DIN EN ISO 16000-9:2008-04

Chamber volume:	0.125 m^3
Temperature:	23 °C ± 1 °C
Relative humidity:	50 % ± 1 %
Air pressure:	normal
Air:	cleaned
Air change rate:	0.5 h^{-1}
Air velocity:	0.3 m/s
Loading:	0.007 m^2/m^3
Specific air flow rate:	71.4 $m^3/(m^2 \cdot h)$
Starting time of the test (t0):	21/10/2022
Air sampling:	3 days after test chamber loading 28 days after test chamber loading

Analytics

Aldehydes and Ketones	DIN ISO 16000-3:2013-01
Limit of quantification:	2 µg/m^3
Volatile Organic Compounds	DIN ISO 16000-6:2022-03
Limit of quantification:	1 µg/m^3 (1,4-Cyclohexanedimethanol, Diethylene glycol, 1,4-Butanediol: 5 µg/m^3)
Note for analysis:	not specified

Remark: It is not permitted to publish extracts of this report and the comments on the first page of this report apply.

1.1 Sample A001, Volatile Organic Compounds after 3 days

Test objective:
Volatile organic compounds (VOC), test chamber, air sampling 3 days after test chamber loading

Test result:

Internal sample number:	57762-A001

No.	Substance	CAS No.	RT [min]	Concentration+ calib. substances ≥ 1 µg/m³ uncalib. substances ≥ 1 µg/m³ DNPH ≥ 2 µg/m³ [µg/m³]	Toluene-equivalent substances ≥ 5 µg/m³ [µg/m³]	CMR Classification++	LCI AgBB 2021 [µg/m³]	R-value
4	**Aliphatic mono alcohols (n-, iso-, cyclo-) and dialcohols**							
4-1	Ethanol	64-17-5	3.73	4	< 5	III5		
4-10	2-Ethyl-1-hexanol	104-76-7	13.40	2	< 5		300	0.01
9	**Acids**							
9-1	Acetic acid	64-19-7	4.52	2	< 5		1200	0.00
13	**Other identified substances in addition to LCI list**							
	Hexamethylcyclotrisiloxane (D3)	541-05-9	8.38	2	< 5			

+ identified and calibrated substances, substance specific calculated
++ classification according to Regulation (EG) N° 1272/2008: Categories Carc. 1A, 1B and 2, Muta. 1A, 1B and 2, Repr. 1A, 1B and 2, TRGS 905: K1A, K1B, K2, M1A, M1B, M2, R1A, R1B, R2; IARC: Group 1, 2A, 2B and 3, DFG MAK-list: Categorie III1 to III5
* unidentified substances, calculated as toluene equivalent reported with significant mass fragments as mass-to-charge ratio (m/z)
n. d.: not determined

Remark: It is not permitted to publish extracts of this report and the comments on the first page of this report apply.

Carcinogenic, mutagenic, and reproductive toxic components*	Concentration after 3 days [µg/m³]	SERa [µg/(m² • h)]
CMR 1: VOC (incl. VVOC and SVOC) with the following categorisations: Regulation (EC) No. 1272/2008: Category Carc. 1A and 1B, Muta. 1A and 1B, Repr. 1A and 1B; TRGS 905: K1A, K1B, M1A, M1B, R1A, R1B; IARC: Group 1 and 2A; DFG (MAK list): Categories III1, III2 (sum)	< 1	< 71
C 1: VOC (incl. VVOC and SVOC) with the following categorisations: Regulation (EG) Nr. 1272/2008: Category Carc. 1A u. 1B; TRGS 905: K1A, K1B (sum)	< 1	< 71

TVOC, Total volatile organic compounds	Concentration after 3 days [µg/m³]	SERa [µg/(m² • h)]
Sum of VOC according to DIN EN 16516	< 5	< 360
Sum of VOC according to AgBB 2021	< 5	< 360
Sum of VOC according to eco-INSTITUT-Label	6	430
Sum of VOC according to ISO 16000-6	9	640

TSVOC, Total semi volatile organic compounds	Concentration after 3 days [µg/m³]	SERa [µg/(m² • h)]
Sum of SVOC according to DIN EN 16516	< 5	< 360
Sum of SVOC without LCI according to AgBB 2021	< 5	< 360
Sum of SVOC without LCI according to eco-INSTITUT-Label	< 1	< 71
Sum of SVOC with LCI according to AgBB 2021	< 5	< 360

TVVOC, Total very volatile organic compounds	Concentration after 3 days [µg/m³]	SERa [µg/(m² • h)]
Sum of VVOC according to AgBB 2021	< 5	< 360
Sum of VVOC according to eco-INSTITUT-Label	4	290

*Excluding formaldehyde and acetaldehyde (Carc. 1B) due to an assumed "practical threshold" under which a significant carcinogenic risk is no longer to be expected (see Federal Institute for Risk Assessment (2006): Toxicological evaluation of formaldehyde and Federal Environment Agency (2016): Reference value for formaldehyde in indoor air and protocol of the 11th meeting of 'Ausschusses für Innenraumrichtwerte' (AIR), 11/2020). In the case of a toxicological emission assessment, a single-substance analysis of the concentrations is necessary.
In the opinion of the committee for Indoor Air Guide Values (Ausschuss für Innenraumrichtwerte) of the Federal Environment Agency, the concentration of 0.1 mg formaldehyde/m³ indoor air, based on a measurement period of half an hour, should not be exceeded, also for a short time (Bundesgesundheitsblatt 2016 · 59: 1040-1044 DOI 10.1007 / s00103 -016-2389-5 © Springer-Verlag Berlin Heidelberg 2016).

Remark: It is not permitted to publish extracts of this report and the comments on the first page of this report apply.

Other sums of VOC	Concentration after 3 days [µg/m³]	SERa [µg/(m² • h)]
VOC without LCI according to AgBB 2021 (sum)	< 5	< 360
VOC without LCI according to eco-INSTITUT-Label (sum)	2	140
CMR 2: VOC (incl. VVOC and SVOC) with the following categorisations: Regulation (EC) No. 1272/2008: Category Carc. 2, Muta. 2, Repr. 2; TRGS 905: K2, M2, R2; IARC: Group 2B; DFG (MAK list): Category III3 (sum)	< 1	< 71
Sensitising compounds with the following categorisations: DFG (MAK list): Category IV; Regulation (EC) No. 1272/2008: skin sensitising, respiratory sensitising; TRGS 907 (sum)	< 1	< 71
Bicyclic Terpenes (sum)	< 1	< 71
C9 - C14 Alkanes / Isoalkanes as dekane-equivalent (sum)	< 1	< 71
C4 - C11 Aldehydes, acyclic, aliphatic (sum)	< 2	< 140
C9 - C15 Alkylated benzenes (sum)	< 1	< 71
Cresols (sum)	< 1	< 71

Risk value for assessment of LCI	R-value
R-value according to eco-INSTITUT-Label	0.01
R-value according to AgBB 2021	0.00
R-value according to Belgian regulation	0.00
R-value according to EU-LCI	0.00

Note:

Due to different requirements in the respective guidelines, the calculation of TVOC, TVVOC, TSVOC and R-value may result in different values.

Short-chain carbonyl compounds (C1-C5) are quantified via HPLC acc. to DIN ISO 16000-3:2013-01. Therefore, no toluene equivalents are given for VVOC. These substances are taken into concern by means of their substance specific calibration via the sum of VVOC acc. to DIN EN 16516:2020-10. For VOC however, the substance specific calibration takes place via HPLC whereas the TVOC is calculated using the toluene equivalent determined via Tenax acc. to DIN EN 16516:2020-10.

Remark: It is not permitted to publish extracts of this report and the comments on the first page of this report apply.

1.2 Sample A001, Volatile Organic Compounds after 28 days

Test objective:
Volatile organic compounds (VOC), test chamber, air sampling 28 days after test chamber loading

Test result:

Internal sample number:	57762-A001

No.	Substance	CAS No.	RT [min]	Concentration+ calib. substances ≥ 1 µg/m³ uncalib. substances ≥ 1 µg/m³ DNPH ≥ 2 µg/m³ [µg/m³]	Toluene-equivalent substances ≥ 5 µg/m³ [µg/m³]	CMR Classification++	LCI AgBB 2021 [µg/m³]	R-value
13	Other identified substances in addition to LCI list							
	Hexamethylcyclotrisiloxane (D3)	541-05-9	9.05	2	< 5			

+ identified and calibrated substances, substance specific calculated
++ classification according to Regulation (EG) N° 1272/2008: Categories Carc. 1A, 1B and 2, Muta. 1A, 1B and 2, Repr. 1A, 1B and 2, TRGS 905: K1A, K1B, K2, M1A, M1B, M2, R1A, R1B, R2; IARC: Group 1, 2A, 2B and 3, DFG MAK-list: Categorie III1 to III5
* unidentified substances, calculated as toluene equivalent reported with significant mass fragments as mass-to-charge ratio (m/z)
n. d.: not determined

Remark: It is not permitted to publish extracts of this report and the comments on the first page of this report apply.

Carcinogenic, mutagenic, and reproductive toxic components*	Concentration after 28 days [µg/m³]	SERa [µg/(m² • h)]
CMR 1: VOC (incl. VVOC and SVOC) with the following categorisations: Regulation (EC) No. 1272/2008: Category Carc. 1A and 1B, Muta. 1A and 1B, Repr. 1A and 1B; TRGS 905: K1A, K1B, M1A, M1B, R1A, R1B; IARC: Group 1 and 2A; DFG (MAK list): Categories III1, III2 (sum)	< 1	< 71
C 1: VOC (incl. VVOC and SVOC) with the following categorisations: Regulation (EG) Nr. 1272/2008: Category Carc. 1A u. 1B; TRGS 905: K1A, K1B (sum)	< 1	< 71

TVOC, Total volatile organic compounds	Concentration after 28 days [µg/m³]	SERa [µg/(m² • h)]
Sum of VOC according to DIN EN 16516	< 5	< 360
Sum of VOC according to AgBB 2021	< 5	< 360
Sum of VOC according to eco-INSTITUT-Label	2	140
Sum of VOC according to ISO 16000-6	10	710

TSVOC, Total semi volatile organic compounds	Concentration after 28 days [µg/m³]	SERa [µg/(m² • h)]
Sum of SVOC according to DIN EN 16516	< 5	< 360
Sum of SVOC without LCI according to AgBB 2021	< 5	< 360
Sum of SVOC without LCI according to eco-INSTITUT-Label	< 1	< 71
Sum of SVOC with LCI according to AgBB 2021	< 5	< 360

TVVOC, Total very volatile organic compounds	Concentration after 28 days [µg/m³]	SERa [µg/(m² • h)]
Sum of VVOC according to AgBB 2021	< 5	< 360
Sum of VVOC according to eco-INSTITUT-Label	< 1	< 71

*Excluding formaldehyde and acetaldehyde (Carc. 1B) due to an assumed "practical threshold" under which a significant carcinogenic risk is no longer to be expected (see Federal Institute for Risk Assessment (2006): Toxicological evaluation of formaldehyde and Federal Environment Agency (2016): Reference value for formaldehyde in indoor air and protocol of the 11th meeting of 'Ausschusses für Innenraumrichtwerte' (AIR), 11/2020). In the case of a toxicological emission assessment, a single-substance analysis of the concentrations is necessary.
In the opinion of the committee for Indoor Air Guide Values (Ausschuss für Innenraumrichtwerte) of the Federal Environment Agency, the concentration of 0.1 mg formaldehyde/m³ indoor air, based on a measurement period of half an hour, should not be exceeded, also for a short time (Bundesgesundheitsblatt 2016 · 59: 1040-1044 DOI 10.1007 / s00103 -016-2389-5 © Springer-Verlag Berlin Heidelberg 2016).

Remark: It is not permitted to publish extracts of this report and the comments on the first page of this report apply.

Other sums of VOC	Concentration after 28 days [µg/m³]	SERa [µg/(m² • h)]
VOC without LCI according to AgBB 2021 (sum)	< 5	< 360
VOC without LCI according to eco-INSTITUT-Label (sum)	2	140
CMR 2: VOC (incl. VVOC and SVOC) with the following categorisations: Regulation (EC) No. 1272/2008: Category Carc. 2, Muta. 2, Repr. 2; TRGS 905: K2, M2, R2; IARC: Group 2B; DFG (MAK list): Category III3 (sum)	< 1	< 71
Sensitising compounds with the following categorisations: DFG (MAK list): Category IV; Regulation (EC) No. 1272/2008: skin sensitising, respiratory sensitising; TRGS 907 (sum)	< 1	< 71
Bicyclic Terpenes (sum)	< 1	< 71
C9 - C14 Alkanes / Isoalkanes as dekane-equivalent (sum)	< 1	< 71
C4 - C11 Aldehydes, acyclic, aliphatic (sum)	< 2	< 140
C9 - C15 Alkylated benzenes (sum)	< 1	< 71
Cresols (sum)	< 1	< 71

Risk value for assessment of LCI	R-value
R-value according to eco-INSTITUT-Label	0.00
R-value according to AgBB 2021	0.00
R-value according to Belgian regulation	0.00
R-value according to EU-LCI	0.00

Note:
Due to different requirements in the respective guidelines, the calculation of TVOC, TVVOC, TSVOC and R-value may result in different values.
Short-chain carbonyl compounds (C1-C5) are quantified via HPLC acc. to DIN ISO 16000-3:2013-01. Therefore, no toluene equivalents are given for VVOC. These substances are taken into concern by means of their substance specific calibration via the sum of VVOC acc. to DIN EN 16516:2020-10. For VOC however, the substance specific calibration takes place via HPLC whereas the TVOC is calculated using the toluene equivalent determined via Tenax acc. to DIN EN 16516:2020-10.

Cologne, 24/11/2022

M. Stein

Michael Stein, Dipl.-Chem.
(Laboratory Management)

Remark: It is not permitted to publish extracts of this report and the comments on the first page of this report apply.

Appendix

Sampling sheet

Laborprüfung

Probenahmebegleitblatt

*Bitte möglichst alle Felder ausfüllen. Sind die mit einem * gekennzeichneten Felder nicht ausgefüllt, können die Prüfstücke nicht zur Laborprüfung angenommen werden.*

57762-001

Bitte pro Probe ein Probenahmebegleitblatt ausfüllen! Die Probenahmeanleitung ist unbedingt einzuhalten!

Auftragserteilung durch* Katharina STAS

Prüflabor eco-INSTITUT Germany GmbH
Schanzenstr. 6-20, Carlswerk 1.19
D - 51063 Köln
Tel. +49 (0)221 - 931245-0
Fax +49 (0)221 - 931245-33

X **Name des Herstellerbetriebes** NMC SA
Gert-Noel-Straße
4731 Eynatten
BELGIEN

Name des Vertriebs (wenn abweichend vom Herstellerbetrieb)

Probenahme durch* (Name, Firma, Telefon)

Probennahmeort*

Prüfstück-/ Artikelbezeichnung* nomafloor M80

Probeart (z.B. Holzwerkstoff Bodenbelag) Sockelleiste

Artikel-Nr. 3044915

Proben-/ Chargen-Nr.* 6000032138

Modell / Programm / Serie nomafloor - Skirtings

Produktionsdatum der Charge* 7/10/2022

Wo wurde die Probe vor Probenahme gelagert? X Fertigung
Lager
Sonstiges

Datum der Probennahme* 10/10/2022

Wie wurde das Produkt vor Probennahme gelagert? X offen
verpackt

Lagerort

Verpackungsmaterial

ggf. zusätzliche Angaben / Besonderheiten zur Probennahme /
Unklarheiten, Fragen, mögliche negative Einflüsse durch Emissionen am Probennahmeort - z.B. Kontaminationen während der Produktion/Lagerung

Bestätigung*
Hiermit wird durch die Unterzeichnung **(Probenahme)** die Richtigkeit der oben gemachten Angaben bestätigt.

Datum (dd/mm/yyyy) 10/10/2022

Unterschrift

Remark: It is not permitted to publish extracts of this report and the comments on the first page of this report apply.

List of calibrated Volatile Organic Compounds (VOC)

Aromatic hydrocarbons (31)
Benzene[4]
1,2,3-Trimethylbenzene
1,2,4-Trimethylbenzene
1,3,5-Trimethylbenzene
1-Isopropyl-2-methylbenzene
1-Isopropyl-4-methylbenzene
1,2,4,5-Tetramethylbenzene
Ethylbenzene
n-Propylbenzene
Isopropylbenzene (Cumene)
1,3-Diisopropylbenzene
1,4-Diisopropylbenzene
n-Butylbenzene
1-Propenylbenzene (beta-Methylstyrene)
Toluene
2-Ethyltoluene
Vinyltoluene
o-Xylene
m-/p-Xylene
Styrene
Phenylacetylene
2-Phenylpropene (alpha-Methylstyrene)
4-Phenylcyclohexene
1-Phenyloctane
1-Phenyldecane[2]
1-Phenylundecane[2]
Indene
Naphthalene
1-Methylnaphthalene
2-Methylnaphthalene
1,4-Dimethylnaphthalene

Aliphatic hydrocarbons (23)
2-Methylpentane[1]
3-Methylpentane[1]
Methylcyclopentane
n-Hexane
Cyclohexane
Methylcyclohexane
1,4-Dimethylcyclohexane
n-Heptane
2,2,4,6,6-Pentamethylheptane
n-Octane
n-Nonane
n-Decane
n-Undecane
n-Dodecane
n-Tridecane
n-Tetradecane
n-Pentadecane
n-Hexadecane
Decahydronaphthalene
1-Octene
1-Decene
1-Dodecene
4-Vinylcyclohexene

Terpenes (12)
delta-3-Carene
alpha-Pinene
beta-Pinene
alpha-Terpinene
Longipinene
Limonene
Longifolene
Isolongifolene
beta-Caryophyllene
alpha-Phellandrene
Myrcene
Camphene

Aliphatic alcohols and ether (18)
Ethanol[1]
1-Propanol[1]
2-Propanol[1]
2-Methyl-1-propanol
1-Butanol
tert-Butanol
1-Pentanol
1-Hexanol
Cyclohexanol
2-Ethyl-1-hexanol
1-Heptanol
1-Octanol
1-Nonanol
1-Decanol
1,4-Cyclohexandimethanol
4-Hydroxy-4-methyl-pentan-2-one (Diacetone alcohol)
Methyl-tert-butyl ether (MTBE)[1]
Tetrahydrofuran (THF)

Aromatic alcohols (phenoles) (8)
Furfuryl alcohol
Benzyl alcohol
Phenol
2-Phenylphenol (oPP)
BHT (2,6-Di-tert-butyl-4-methylphenol)
o-Cresol
m-/p-Cresol
4-Chloro-3-methylphenol (Chlorocresol)

Glycols, Glycol ether, Glycol ester (49)
Ethyleneglycol (Ethan-1,2-diol)
Propylenglycol (Propane-1,2-diol)
Diethylene glycol
Dipropylene glycol
Neopentyl glycol
Hexyleneglycol
Ethyldiglycol
Ethylene glycol monobutyl ether
Diethylene glycol methyl ether
Diethylene glycol monobutyl ether
Diethylene glycol phenyl ether
Dipropylene glycol-dimetyl ether
Dipropylene glycol mono-n-butyl ether
Dipropylene glycol mono-tert-butyl ether
Dipropylene glycol monomethyl ether
Dipropylene glycol mono-n-propyl ether
Tripropylene glycol monomethyl ether
Triethylene glycol dimethyl ether
1,2-Propylene glycol dimethyl ether
1,2-Propylene glycol-n-propyl ether
1,2-Propylene glycol-n-butyl ether
Butyl glycolate
2-Methoxyethanol
2-Ethoxyethanol
2-Methylethoxyethanol
2-Propoxyethanol
2-Hexoxyethanol
2-(2-Hexoxyethoxy)ethanol
2-Phenoxyethanol
1-Methoxy-2-propanol
2-Methoxy-1-propanol
1-Ethoxy-2-propanol
1-tert-Butoxy-2-propanol
3-Methoxy-1-butanol
1,4-Butanediol
1,2-Dimethoxyethane
1,2-Diethoxyethane
1-Methoxy-2-(2-methoxy-ethoxy)ethane
Ethylene carbonate
Propylene carbonate
2-Methoxy-1-propyl acetate
Diethylene glycol monomethyl ether acetate
2-Methoxyethyl acetate
2-Ethoxyethyl acetate
2-Butoxy ethyl acetate
Dipropylene glycol monomethyl ether acetate
Propylene glycol diacetate
Texanol
TXIB (Texanol isobutyrate)

Aldehydes (26)
Formaldehyde[1,3,4]
Acetaldehyde[1,3,4]
Propanal[1,3]
Butanal[1,3]
3-Methyl-1-butanal
Pentanal
Hexanal
2-Ethylhexanal
Heptanal
Octanal
Nonanal
Decanal
Propenal (Acrolein)[1,3]
Isobutenal (Methacrolein)[3]
2-Butenal[3]
2-Pentenal[3]
2-Hexenal
2-Heptenal
2-Octenal

Remark: It is not permitted to publish extracts of this report and the comments on the first page of this report apply.

2-Nonenal
2-Decenal
2-Undecenal
Ethanedial (Glyoxal)[1,3]
Glutaraldehyde
Furfural
Benzaldehyde

Ketones (14)
Acetone[1,3]
1-Hydroxyacetone
Ethylmethylketone[3]
Methylisobutylketone
3-Methyl-2-butanone
Cyclopentanone
2-Methylcyclopentanone
Cyclohexanone
2-Methylcyclohexanone
2-Hexanone
2-Heptanone
Acetophenone
Isophorone
Benzophenone[2]

Acids (11)
Acetic acid
Propionic acid
Pivalic acid
Butyric acid
Isobutyric acid
n-Valeric acid
n-Caproic acid
2-Ethylhexanoic acid
n-Heptanoic acid
n-Octanoic acid
Neodecanoic acid

Esters and Lactones (31)
Methyl acetate[1]
Ethyl acetate[1]
Vinyl acetate[1]
Propyl acetate
Isopropyl acetate
2-Methoxy-1-methylethyl acetate
n-Butyl acetate
Isobutylacetate
2-Ethylhexyl acetate
n-Butyl formate
Methyl acrylate
Methyl methacrylate
Butyl methacrylate
Ethyl acrylate
n-Butyl acrylate
2-Ethylhexyl acrylate
Hexanediol diacrylate
Dipropylene glycol diacrylate
Dimethyl succinate
Dimethyl glutarate
Dimethyl adipate
Dibutyl fumarate
Dibutyl maleate
Diisobutyl succinate
Diisobutyl glutarate
Butyrolactone
Dimethyl phthalate
Diethyl phthalate[2]
Dipropyl phthalate[2]
Dibutyl phthalate[2]
Diisobutyl phthalate[2]

Chlorinated hydrocarbons (17)
Dichloromethane[1]
Trichloromethane (Chloroform)[4]
Tetrachloromethane
1,2-Dichloroethane[4]
1,1,1-Trichloroethane
2-Chloropropane
1,2,3-Trichloropropane[4]
Trichloroethene[4]
Tetrachloroethene
trans-1,3-Dichloropropene[4]
cis-1,3-Dichloropropene[4]
Chloroprene[4]
1,3-Dichloro-2-propanol[4]
Chlorobenzene
1,4-Dichlorobenzene
alpha-Chlorotoluene[4]
alpha,alpha,alpha-Trichlorotoluene[4]

Cyclic siloxanes (5)
Hexamethylcyclotrisiloxane (D3)
Octamethylcyclotetrasiloxane (D4)
Decamethylcyclopentasiloxane (D5)
Dodecamethylcyclohexasiloxane (D6)
Tetradecamethylcycoheptasiloxane (D7)

Others (41)
1,4-Dioxane[4]
1,2-Dibromoethane[4]
2-Nitropropane[4]
2,3-Dinitrotoluene[4]
2,4-Dinitrotoluene[4]
2,6-Dinitrotoluene[4]
3,4-Dinitrotoluene[2,4]
o-Anisidine[4]
o-Toluidine[4]
4-Chloro-o-toluidine[4]
5-Nitro-o-toluidine[2]
Acrylonitrile[1,4]
2,2'-Azobisisobutyronitrile
Tetramethylsuccinonitrile
Azobenzene[2,4]
Caprolactam
Furan[1,4]
2-Methylfuran
2-Pentylfuran
Methenamine
Triethylamine
2-Butanonoxime[4]
Triethyl phosphate
Tributyl phosphate[2]
5-Chloro-2-methyl-4-isothiazolin-3-one (CIT)
2-Methyl-4-isothiazolin-3-one (MIT)
2-n-Octyl-4-isothiazolin-3-one (OIT)[2,4]
Formamide
Dimethylformamide (DMF)
Acetamide
N-Nitrosopyrrolidine[4]
N-Methyl-2-pyrrolidone
N-Ethyl-2-pyrrolidone
N-Butyl-2-pyrrolidone
Aniline
4-Chloroaniline[4]
2-Nitroanisole[4]
Cyclohexyl isocyanate
p-Cresidine[4]
Diethyl sulfate[4]
Epichlorohydrin[4]

1 VVOC
2 SVOC
3 Analysis acc. to DIN ISO 16000-3:2013-01 (DNPH)
4 Carcinogens, category 1A and 1B according to Regulation (EC) No 1272/2008 and TRGS 905

Remark: It is not permitted to publish extracts of this report and the comments on the first page of this report apply.

Definition of terms

VOC (volatile organic compounds)	All individual compounds with a concentration ≥ 1 µg/m³ in the retention range C_6 (n-Hexane) to C_{16} (n-Hexadecane)
TVOC	Total volatile organic compounds
TVOC according to DIN EN 16516	Sum of all VOC ≥ 5 µg/m³ in the retention range C_6 to C_{16}, calculated as toluene equivalent (used, among others, with M1)
TVOC according to AgBB	Sum of all identified and calibrated VOC ≥ 5 µg/m³ with LCI and not calibrated VOC ≥ 5 µg/m³ calculated as toluene equivalent (also used, among others, for the Blue Angel)
TVOC according to eco-INSTITUT-Label	Sum of all identified and calibrated VOC ≥ 1 µg/m³ and not calibrated VOC ≥ 1 µg/m³ calculated as toluene equivalent (also used for natureplus)
TVOC according to DIN ISO 16000-6	Total area of chromatogram in the retention range C_6 to C_{16}, calculated as toluene equivalent (used, among others, by CDPH, BIFMA or the French VOC Regulation)
TVOC without LCI according to AgBB	Sum of all VOC without NIK ≥ 5 µg/m³ in the retention range C_6 to C_{16}
TVOC without LCI according to eco-INSTITUT-Label	Sum of all VOC without NIK ≥ 1 µg/m³ in the retention range C_6 to C_{16}
CMR-VOC (carcinogenic, mutagenic, reproduction-toxic VOC, VVOC and SVOC)	All individual substances with the following categories: Regulation (EC) No. 1272/2008: Category Car.1A and 1B, Muta. 1A and 1B, Repr. 1A and 1B TRGS 905: K1A, K1B, M1A, M1B, R1A, R1B IARC: Group 1 and 2A DFG (MAK lists): Category III1and III2
VVOC (very volatile organic compounds)	All individual substances with a concentration ≥ 1 µg/m³ in the retention range < C_6
TVVOC	Total very volatile organic compounds
TVVOC according to AgBB	Sum of all identified and calibrated VVOC ≥ 5 µg/m³ with LCI
TVVOC according to eco-INSTITUT-Label	Sum of all identified and calibrated VVOC ≥ 1 µg/m³ with LCI
SVOC (semi volatile organic compounds)	All individual substances ≥ 1 µg/m³ in the retention range C_{16} (n-hexadecane) to C_{22} (docosane)
TSVOC	Total semi volatile organic compounds
TSVOC according to DIN EN 16516	Sum of all SVOC in the retention range C_{16} to C_{22}, calculated as toluene equivalent
TSVOC without LCI according to AgBB	Sum of all SVOC ≥ 5 µg/m³ without LCI
TSVOC without LCI according to eco-INSTITUT-Label	Sum of all SVOC ≥ 1 µg/m³ without LCI
TSVOC with LCI according to AgBB	Sum of all substance-specific calibrated and SVOC ≥ 5 µg/m³ with LCI
SER	Specific emission rate (see "Explanation of Specific Emission Rate SER")
LCI value	Lowest Concentration of Interest; calculated value for the evaluation of VOC, established by the Committee for Health-related Evaluation of Building Products (Ausschuss zur gesundheitlichen Bewertung von Bauprodukten - AgBB)

Remark: It is not permitted to publish extracts of this report and the comments on the first page of this report apply.

R value	The quotient of the concentration and the LCI value is generated for every substance which is detected in the test chamber air. The sum of the calculated quotients results in the R value.
R value according to eco-INSTITUT-Label	R value for all identified substances ≥ 1 µg/m³ with LCI, established by the AgBB
R value according to AgBB	R value for all identified substances ≥ 5 µg/m³ with LCI, established by the AgBB
R value according to Belgian regulation	R value for all identified substances ≥ 5 µg/m³ with LCI, established by the Belgian regulation
R value according to EU-LCI	R value for all identified substances ≥ 5 µg/m³ with EU-LCI value, established by the European Commission
RT (retention time)	Time for a particular analyte to pass through the system (from the column inlet to the detector)
CAS No. (Chemical Abstracts Service)	International unique numerical identifier for a chemical substance
Toluene equivalent	Concentration of the substance detected in the test chamber air for which the quantification was carried out with regard to toluene.

Remark: It is not permitted to publish extracts of this report and the comments on the first page of this report apply.

Commentary on emission analysis

Test method

Measurement of the volatile organic compounds takes place in the test chamber in conditions similar to those applying in practice. Standardized test conditions are defined for the test chamber regarding loading, air exchange, relative humidity, temperature, and incoming air, based on the type of test specimen and the required guideline. These conditions and the underlying standards are to be found in the section on test methods in the laboratory report.

Air samples are taken from the test chamber at defined points in time during the continuously running test. To this end, approximately 5 L of air are collected from the test chamber at an air flow rate of 100 mL/min on Tenax and approx. 100 L at an air flow rate of 0.8 L/min on silica gel coated with DNPH (2,4-dinitrophenylhydrazine).

After thermal desorption, the substances adsorbed on Tenax are analysed using gas chromatographic separation and mass spectrometric determination. The gas chromatographic separation is performed with a slightly polar capillary column of 60 m in length.

The substances derivatized with DNPH for the determination of formaldehyde and other short-chain carbonyl compounds (C1 - C6) are analysed using high-performance liquid chromatography (HPLC).

Over 200 compounds, including volatile organic compounds (C6 - C16), semi-volatile organic compounds (C16 - C22) and – insofar as possible with this method – also very volatile organic compounds (less than C6) are determined and quantified individually.

All other substances – insofar as is possible – are identified through comparison with a library of spectra. The quantification of these substances and non-identified substances is performed through a comparison of their signal area with the signal of toluene.

The determined substance concentrations are corrected using the recovery rate of the internal standard (toluene-d8). Identification and quantification of substances is carried out from a concentration (limit of quantification) of 1 µg per m³ test chamber air or 2 µg/m³ for DNPH-derivatised substances. In the case of highly loaded samples, the evaluation limit of non-calibrated substances is raised in some cases, as it is no longer possible to assign individual, small signals due to the large number of signals.

Quality assurance

The eco-INSTITUT Germany GmbH is granted flexible scope of accreditation pursuant to DIN EN ISO/IEC 17025:2018-03. The accreditation covers the analytical determination of all volatile organic compounds, including the test chamber method.

In each analysis the analytical system is checked using an external standard based on the specifications in standard DIN EN 16516:2020-10. The stability of the analytical systems is documented based on the test standard using control charts.

Laboratory performance is assessed at least once a year in inter-laboratory comparisons by comparing the results with those obtained by other laboratories for identical samples.

A blank is run prior to introducing the test specimen into the test chamber to check for the possible presence of volatile organic compounds.

The expanded measurement uncertainty U for the analytical determination of all volatile organic compounds, including the test chamber method, is estimated to 41.7 %. The calculation is based on DIN ISO 11352:2013-03 (Nordtest).

Remark: It is not permitted to publish extracts of this report and the comments on the first page of this report apply.

Explanation of Specific Emission Rate SER

Emission measurements are accomplished in test chambers under defined physical conditions (temperature, relative humidity, room loading, air change rate etc.).

Test chamber measurement results are directly comparable only if the investigations were accomplished under the same basic conditions.

If the differences of the physical conditions refer only to the change of air rate and/or the loading, the "SER" or "specific emission rate" can be used for comparability of the measurement results. The SER indicates how many volatile organic compounds (VOC) are released by the sample for each material unit and hour (h).

The SER can be calculated using the formula below for each proven individual component of the VOC from the data in the test report.

As material units the following are applicable:

l = unit of length (m)	relation between emission and length
a = unit area (m^2)	relation between emission and surface
v = unit volume (m^3)	relation between emission and volume
u = piece unit (unit = piece)	relation between emission and complete unit

From this the different dimensions for SER result:

length-specific	SER_l	in µg/(m·h)
surface-specific	SER_a	in µg/(m^2·h)
volume-specific	SER_v	in µg/(m^3·h)
unit specific	SER_u	in µg/(u·h)

SER thus represents a product specific rate, which describes the mass of the volatile organic compound, which is emitted by the product per time unit at a certain time after beginning of the examination.

$$SER = q \cdot c$$

q specific air flow rate (quotient from change of air rate and loading)

c concentration of the measured substance(s)

The result can be indicated in milligrams (mg) in place of micro grams (µg), whereby 1 mg = 1000 µg.

Remark: It is not permitted to publish extracts of this report and the comments on the first page of this report apply.